



Approval body for construction products and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and Laender Governments



European Technical Assessment

ETA-11/0514 of 17 May 2018

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:

Trade name of the construction product

Product family to which the construction product belongs

Manufacturer

Manufacturing plant

This European Technical Assessment contains

This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of

Deutsches Institut für Bautechnik

Injection system VMU plus for rebar connections

Systems for post-installed rebar connections with mortar

MKT

Metall-Kunststoff-Technik GmbH & Co. KG Auf dem Immel 2 67685 Weilerbach DEUTSCHLAND

Werk 1,D Werk 2,D

22 pages including 3 annexes which form an integral part of this assessment

EAD 330087-00-0601



European Technical Assessment ETA-11/0514

Page 2 of 22 | 17 May 2018

English translation prepared by DIBt

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Z22622.18 8.06.01-125/18



European Technical Assessment ETA-11/0514

English translation prepared by DIBt

Page 3 of 22 | 17 May 2018

Specific Part

1 Technical description of the product

The subject of this European Technical Assessment is the post-installed connection, by anchoring or overlap connection joint, of reinforcing bars (rebars) in existing structures made of normal weight concrete, using the "Injection system VMU plus for rebar connection" in accordance with the regulations for reinforced concrete construction.

Reinforcing bars made of steel with a diameter ϕ from 8 to 32 mm or the tension anchor ZA from sizes M12 to M24 according to Annex A and injection mortar VMU plus are used for rebar connections. The rebar is placed into a drilled hole filled with injection mortar and is anchored via the bond between rebar, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the rebar connection of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance under static and quasi-static loading	See Annex C 1

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C 2 and C 3

Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with European Assessment Document EAD No. 330087-00-0601, the applicable European legal act is: [96/582/EC].

The system(s) to be applied is (are): 1

Z22622.18 8.06.01-125/18



European Technical Assessment ETA-11/0514

Page 4 of 22 | 17 May 2018

English translation prepared by DIBt

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 17 May 2018 by Deutsches Institut für Bautechnik

BD Dipl.-Ing. Andreas Kummerow Head of Department

beglaubigt: Baderschneider

Z22622.18 8.06.01-125/18




Cartridge: Injection Adhesive VMU plus

150 ml, 280 ml, 333 ml and 380 ml to 420 ml cartridge (Type: "coaxial")




Imprint: VMU plus, processing notes, chargecode, shelf life, hazard-code, storage temperature, curing- and working time (depending on the temperature), optional with travel scale

235 ml, 345 ml and 825ml injection mortar cartridge (Type: "side-by-side")



Imprint: VMU plus, processing notes, chargecode, shelf life, hazard-code, storage temperature, curing- and working time (depending on the temperature), optional with travel scale

Tension anchor ZA: M12, M16, M20, M24



Reinforcing bar: Ø8, Ø10, Ø12, Ø14, Ø16, Ø20, Ø22, Ø24, Ø25, Ø28, Ø32



Injection System VMU plus for rebar connections

Product description


Injection Adhesive with tension anchor ZA or reinforcing bar

Annex A1

Application examples of post-installed rebar

English translation prepared by DIBt












Table A1: Material

Part	Description		Material										
		ZA vz			ZA A4				Tension anchor ZA				
Tens	sion anchor ZA	M12 M16	M20	M24	M12	M16	M20	M24	M12	M16	M20	M24	
1	Rebar	Class B according $f_{uk} = f_{tk} = k \cdot f_{yk}$	Class B according to NDP or NCL acc. to EN 1992-1 $t_{uk} = f_{tk} = k \cdot f_{yk}$					992-1-	1/NA				
2	Threaded rod	Steel, zinc plated acc. to EN 10087:1998 or EN 10263:2001			1.440	Stainless steel, 1.4362, 1.4401, 1.4404, 1.4571, EN 10088:2014			High corrosion resist steel 1.4529, 1.4565 EN 10088:2014				
	f _{yk} [N/mm²]	640				640	560		640			560	
3	Washer	Steel, zinc pl	ated		Stainless steel				High corrosion resistant steel				
4	Hexagon nut	Steel, zinc plated acc. to EN 10087:1998 or EN 10263:2001			1.440		eel, 1.4 04, 1.4 014	-	steel,	corrosio 1.4529 0088:20	9, 1.456		
Reba	Rebar												
5	Rebar Bars and de-coiled rods class B or C f_{yk} and k according to NDP or NCL of EN 1992-1-1/NA $f_{uk} = f_{tk} = k \cdot f_{yk}$												

Figure A9: Tension anchor ZA: M12, M16, M20, M24




Figure A10: Rebar Ø8, Ø10, Ø12, Ø14, Ø16, Ø20, Ø22, Ø24, Ø25, Ø28, Ø32



- Minimum value of related rip area f_{R,min} according to EN 1992-1-1:2004+AC:2010
- Rib height of the bar shall be in the range $0.05\varnothing \le h \le 0.07\varnothing$

(∅: Nominal diameter of the bar; h: Rip height of the bar)

Injection System VMU plus for rebar connections	
Product description Material / Marking	Annex A4



Specifications of intended use

Anchorages subject to:

Rebar	Ø8	Ø10	Ø12	Ø14	Ø16	Ø20	Ø22	Ø24	Ø25	Ø28	Ø32
Static or quasi-static action	✓										
Fire exposure						✓					

Tension anchor ZA	M12	M24			
Static or quasi-static action	√				
Fire exposure	√				

Base material:

- Reinforced or unreinforced normal weight concrete acc. to EN 206-1:2000
- Strength classes C12/15 to C50/60 acc. to EN 206-1:2000
- Maximum chloride concrete of 0,40 % (CL 0,40) related to the cement content acc. to EN 206-1:2000
- Non-carbonated concrete

Note: In case of a carbonated surface of the existing concrete structure the carbonated layer shall be removed in the area of the post-installed rebar connection with a diameter of \emptyset + 60 mm prior to the installation of the new rebar. The depth of concrete to be removed shall correspond to at least the minimum concrete cover in accordance with EN 1992-1-1:2004+AC:2010.

The foregoing may be neglected if building components are new and not carbonated and if building components are in dry conditions.

Temperature range:

- 40 °C to +80 °C (max. short term temperature +80 °C and max. long term temperature +50 °C)

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc plated steel, stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions exist (high corrosion resistant steel)

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used)

Injection System VMU plus for rebar connections	
Intended use Specification of intended use	Annex B1



Specifications of intended use

Design:

- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored
- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work
- Anchorages are designed in accordance with EN 1992-1-1:2004+AC:2010, EN 1992-1-2:2004+AC:2008 and Annex B3 and B4
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing

Installation:

- · Dry or wet concrete
- · Installation in water filled bore holes is not admissible
- Overhead installation admissible
- · Hole drilling by hammer drill, vacuum drill or compressed air drill
- Check the position of the existing rebars (if the position of existing rebars is not known, it shall be
 determined using a rebar detector suitable for this purpose as well as on the basis of the construction
 documentation and then marked on the building component for the overlap joint)
- · The joints for concreting must be roughened to at least such an extent that aggregate protrude
- The installation of post-installed rebar or tension anchor ZA shall be done only by suitable trained installer and under supervision on site; the conditions under which an installer may be considered as suitable trained and the conditions for supervision on site are up to the member states in which the installation is done
- Minimum concrete cover acc. to EN 1992-1-1:2004+AC:2010 must be observed


Injection System VMU plus for rebar connections	
Intended use Specification of intended use	Annex B2



General construction rules for tension anchor ZA

- The length for the post-installed thread must not be added to the anchoring length
- The tension anchor ZA can only transfer forces towards the bar axis
- Tension forces must be transferred by an overlap joint into the present reinforcement of the member
- The transmission of shear forces must be ensured by additional measures, e.g. by shear cleats or anchors with an European Technical Assessment (ETA)
- In the anchor plate the holes for the tension anchors must be executed as elongated holes with axis in the direction of the shear force
- If the clear distance of overlapping bars is greater than 4Ø, the lap length must be increased by a length equal to the clear space where it exceeds 4Ø

Figure B1: Tension Anchor ZA



- c concrete cover of tension anchor ZA
- c₁ concrete cover at front end of cast-in-place rebar
- c₂ Length of bonded thread

min c minimum concrete cover according Table B1 and EN 1992-1-1:2004+AC:2010

- Ø diameter of tension anchor (rebar part)
 d diameter of tension anchor (threaded part)
- ℓ₀ lap length acc. to EN 1992-1-1:2004+AC:2010
- ℓ_v embedment depth $\ell_v \ge \ell_0 + c_1$
- ℓ_{ges} overall embedment depth $\ell_{ges} \ge \ell_0 + c_2$
- d₀ nominal drill bit diameter according to Table B6


Injection System VMU plus for rebar connections	
Intended use General construction rules (Tension anchor ZA)	Annex B3



General construction rules for post-installed rebars

- The shear transfer between old and new concrete shall be designed acc. to EN 1992-1-1:2004+AC:2010
- Only tension forces in the axis of the rebar may be transmitted
- If the clear distance of overlapping bars is greater than 4Ø, the lap length must be increased by a length equal to the clear space where it exceeds 4Ø

Figure B2: Post-installed rebars



c concrete cover of post-installed rebar

concrete cover at front end of cast-in-place rebar

min c minimum concrete cover according Table B1 and EN 1992-1-1:2004+AC:2010

Ø diameter of tension anchor (rebar)

lap length acc. to EN 1992-1-1:2004+AC:2010

 ℓ_{v} embedment depth $\ell_{v} \ge \ell_{0} + c_{1}$

d₀ nominal drill bit diameter according to Table B6

Injection System VMU plus for rebar connections	
Intended use General construction rules (post-installed rebar)	Annex B4



Table B1: Minimum concrete cover min c¹⁾ of post-installed rebar and tension anchor ZA depending on drilling method

Drilling method	Rod diameter	min c (with drilling aid device)		
Hammer drilling	< 25 mm	30 mm+ 0,06 • ℓ _v ≥ 2 Ø	30 mm+ 0,02 • ℓ _v ≥ 2 Ø	
Vacuum drilling	≥ 25 mm	40 mm+ 0,06 • ℓ _v ≥ 2 Ø	40 mm+ 0,02 • ℓ _v ≥ 2 Ø	
Compressed air	< 25 mm	50 mm+ 0,08 • ℓ _v	50 mm+ 0,02 • ℓ _v	
drilling	≥ 25 mm	60 mm+ 0,08 • ℓ _v	60 mm+ 0,02 • ℓ _v	

¹⁾ See Annex B3 and B4; Minimum concrete cover acc. to EN 1992-1-1:2004+AC:2010 must be observed.




Table B2: Dimensions and installation parameters of tension anchor ZA

Anchor size	M12	M16	M20	M24			
Thread diameter	d	[mm]	12	16	20	24	
Rebar diameter	Ø	[mm]	12	16	20	25	
Cross section area (threaded part)	As	[mm ²]	84	157	245	353	
Width across nut flats	SW	[mm]	19	24	30	36	
Effective embedment depth	ℓ _v	[mm]	according to static calculation				
steel, zinc Length of bonded thread plated	C ₂	[mm]	≥ 20	≥ 20	≥ 20	≥ 20	
A4/HCR	- 2		≥ 100	≥ 100	≥ 100	≥ 100	
Maximum installation torque	T _{inst}	[Nm]	50	100	150	150	

Injection System VMU plus for rebar connections	
Intended use Minimum concrete cover / Installation parameters ZA	Annex B5



Table B3: Working and curing time

Bore hole temperature	Cartridge temperature	Working time	Minimum	curing time
			dry concrete	wet concrete
-10°C to -6°C	≥ +15°C	90 min	24 h	48 h
- 5°C to - 1°C		90 min	14 h	28 h
0°C to + 4°C	500 : 0500	45 min	7 h	14 h
+ 5°C to + 9°C		25 min	2 h	4 h
+ 10°C to + 19°C	+5°C to +25°C	15 min	80 min	160 min
+ 20°C to + 24°C		6 min	45 min	90 min
+ 25°C to + 29°C		4 min	25 min	50 min
+ 30°C to + 40°C	≤ +20°C	2,5 min	15 min	30 min

Table B4: Dispensing tools

	Cartridge		111	
Туре	Size	Han	d tool	Pneumatic tool
coaxial	150, 280, 333 ml	e.g.: V	e.g.: VM-P 345 Pneumatic	
соа	380 to 420 ml	e.g.: VM-P 380	e.g.: VM-P 380 Profi	e.g.: VM-P 380 Pneumatic
/-side	235, 345 ml	e.g.: VM-P 345	e.g.: VM-P 345 Profi	e.g.: VM-P 345 Pneumatic
side-by-side	825 ml	-	-	e.g.: VM-P 825 Pneumatic

All cartridges can also be extruded by battery tool (e.g. VM-P Akku)


Injection System VMU plus for rebar connections	
Intended use Working and curing time / dispensing tools	Annex B6



Table B5: Drilling and cleaning

		Drill bit diameter	Brush	diameter
	Rebar ZA	Drill bit diameter	Brush- Ø	min. Brush-Ø
_ ~	ZA	d ₀	d _b	d _{b,min}
[mm]	[-]	[mm]	[mm]	[mm]
8		12	14	12,5
10		14	16	14,5
12	M12	16	18	16,5
14		18	20	18,5
16	M16	20	22	20,5
20	M20	25	27	25,5
22		28	30	28,5
24		32	34	32,5
25	M24	32	34	32,5
28		35	37	35,5
32		40	43	40,5

Compressed air hose (min. 6 bar) with air valve







Brush RB Brush extension SDS Plus Adapter


Retaining washer VM-IA

Extension pipe

Static mixer







Injection System VMU plus for rebar connections

Intended use

Cleaning and installation tools


Annex B7



Table B6: Installation tools and max. embedment depth

Dahan	Tension	Drill bit			Cartric all for	Cartridge: side-by-side (825 ml)			
Rebar Ø	anchor ZA	diameter d ₀	Retaining washer 1)	Hand- or akku-tool		nd- or akku-tool Compressed air tool		Compressed air tool	
			Washer	$\ell_{v,max}$	max Extension		Extension	$\ell_{v,max}$	Extension
[mm]	[-]	[mm]		[cm]	pipe	[cm]	pipe	[cm]	pipe
8		12	-			80		80	
10		14	VM-IA 14	70	VM-XE 10	100	70 VM-XE 10	100	VM-XE 10
12	M12	16	VM-IA 16					120	
14		18	VM-IA 18			100		140	
16	M16	20	VM-IA 20					160	
20	M20	25	VM-IA 25			70			
22		28	VM-IA 28		VM-XE 10	70		200	VM-XLE 16
24		32	VM-IA 32	50 VM-XLE 16	VM-XLE 16		VM-XLE 16	200	AIM-VEE 10
25	M24	32	VM-IA 32		50				
28		35	VM-IA 35			50		200	
32		40	VM-IA 40					200	

¹⁾ For horizontal or overhead installation as well as for drill holes deeper than 240mm



On the static mixer and the extension pipe the mortar filling mark l_m and the drill hole depth h_1 must be marked with an adhesive tape or text marker. Rough estimate: $l_m = \frac{1}{3} \cdot h_1$ Fill in the mortar as long until the filling mark l_m will be visible.

Optimal mortar volume:
$$l_m = h_1*(1,2*\frac{\phi^2}{d_0^2}-0,2)$$
 [mm]


- l_m Length from the end of the retaining washer to the mark on the mixer extension
- h_1 drill hole depth = embedment depth ℓ_v resp. ℓ_{ges})
- Ø rebar diameter
- do nominal drill bit diameter

Injection System VMU plus for rebar connections	
Intended use Installation tools, max. embedment depth, marking of extension pipe	Annex B8




Installation instructions

Bore hole drilling



Drill hole by hammer drilling, vacuum drilling or compressed air drilling (with drill bit diameter according to Annex B7 and selected embedment depth). In case of aborted holes, the bore holes must be filled with mortar.

Cleaning



Starting from the bottom or back of the bore hole, blow out the hole with compressed air (min. 6 bar) (Annex B7) a minimum of **four** times until return air stream is free of noticeable dust.

If bore hole ground is not reached, an extension must be used.

Brush the hole with an appropriate sized wire brush $\geq d_{b,min}$ (Table B5, check minimum brush diameter $d_{b,min}$) a minimum of **four** times with rotary motion. If bore hole ground is not reached, a brush extension must be used.

Starting from the bottom or back of the bore hole, blow out the hole with compressed air (min. 6 bar) again a minimum of **four** times until return air stream is free of noticeable dust.

If bore hole ground is not reached, an extension must be used.

Injection System VMU plus for rebar connections

Intended use

Installation instruction
Bore hole drilling and cleaning

Annex B9

8



Installation instruction (continuation) Preparing and injection into borehole 3 Mark the position of the embedment depth on the rebar (e.g. with tape) Check drill hole depth by inserting rebar or anchor rod into the empty hole. 4 Prepare cartridge with static mixer (if necessary with extension pipe and retaining washer). Attach the supplied static-mixing nozzle to the cartridge and load the 5 cartridge into the correct dispensing tool. For every working interruption longer than the recommended working time (Table B3) as well as for new cartridges, a new static-mixer shall be used. Prior to applying, discard mortar (forerun) until the mortar shows a consistent grey 6 min.3x colour, but at least three full strokes. Never use this mortar! Fill in injection mortar from the bottom of the clean borehole approx. 2/3 air bubble free. Slowly moving the static mixer out of the borehole prevents the formation of 7 air inclusions. For embedment larger than 190mm an extension pipe (Table B6) must be used.

Injection System VMU plus for rebar connections	
Intended use Installation instruction (continuation) Preparing and injection into the borehole	Annex B10

retaining washer shall be used.

For overhead and horizontal installation and embedment larger than 240mm a



Installation instruction (continuation)

Installation of rebar or tension anchor Immediately insert the rebar or tension anchor into the hole while turning slightly 7 until the embedment depth is reached. The bar shall be free of dirt, grease and oil. Excess injection mortar must exceed from the borehole, the annular gap shall be filled completely with mortar. If no mortar exceeds, these requirements are not 8 maintained and the application has to be renewed. For overhead installation fix embedment part (e.g. wedges). Ensure the curing time of the injection mortar according to table B3. 9 Attention: the working time may vary due to different underground temperatures. Do not move or load the anchor or rebar until curing time. 10 After the curing time the threaded rod or reinforcing bar can be load.

Injection System VMU plus for rebar connections	
Intended use Installation instruction (continuation) Installation of rebar or tension anchor	Annex B11



Minimum anchorage length and minimum lap length

The minimum anchorage length $\ell_{\text{b,min}}$ and the minimum lap length $\ell_{\text{0,min}}$ according to EN 1992-1-1:2004+AC:2010 ($\ell_{\text{b,min}}$ acc. to Eq. 8.6 and Eq. 8.7 and $\ell_{\text{0,min}}$ acc. to Eq. 8.11) shall be multiplied by the amplification factor α_{lb} acc. to Table C1.

Table C1: Amplification factor α_{lb} depending on concrete strength class and drilling method

Concrete strength class	Drilling method	Rod diameter	Amplification factor α_{lb} [-]
C12/15 to C50/60	hammer drilling vacuum drilling compressed air drilling	Ø8 to Ø32 ZA-M12 to ZA-M24	1,0

Table C2: Reduction factor k_b for all drilling methods

Rod diameter		Concrete strength class						
		C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50
Ø8 to Ø25 ZA-M12 to ZA-M24	k _b [-]	1,0						
Ø28 to Ø32	k _b [-]	1,0 0,92 0						0,86

Table C3: Design values of the ultimate bond stress f_{bd,PIR} in N/mm² for all drilling methods and for good bond conditions

 $f_{bd,PIR} = k_b \cdot f_{bd}$

with

 f_{bd} : Design value of the ultimate bond stress in N/mm² considering the concrete strength classes and the rebar diameter according to EN 1992-1-1:2004+AC:2010

(for all other bond conditions multiply the values by 0,7)

k_b: Reduction factor according to Table C2

Rod diameter		Concrete strength class								
		C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
Ø8 to Ø25 ZA-M12 to ZA-M24	f _{bd,PIR} [N/mm²]	1,6	2,0	2,3	2,7	3,0	3,4	3,7	4,0	4,3
Ø28 to Ø32	f _{bd,PIR} [N/mm²]	1,6	2,0	2,3	2,7	3,0	3,4	3,7	3,7	3,7

Injection System VMU plus for rebar connections	
Performances Amplification factor a _{lb} Design values of ultimate bond resistance f _{bd,PIR}	Annex C1



Design value of ultimate bond stress $f_{bd,fi}$ under fire exposure for concrete classes C12/15 to C50/60 (all drilling methods):

The design value of ultimate bond stress f_{bd,fi} under fire exposure will be calculated by the following equation:

$$\begin{aligned} f_{bd,fi} &= k_{fi}(\theta) \cdot f_{bd,PIR} \cdot \gamma_c / \gamma_{M,fi} \\ &\text{with: } \theta \leq 243^{\circ}\text{C:} \quad k_{fi}(\theta) = 18,88 * \theta^{(\theta^* \cdot 0.016)} / \left(f_{bd,PIR} * 4,3 \right) \leq 1,0 \end{aligned}$$

 $\theta > 243^{\circ}C$: $k_{fi}(\theta) = 0$

f_{bd,fi} design value of ultimate bond stress in case of fire in N/mm²

 $\begin{array}{ll} \theta & & \text{Temperature in °C in the mortar layer} \\ k_{\text{fi}}(\theta) & & \text{Reduction factor under fire exposure} \end{array}$

f_{bd,PIR} Design value of the ultimate bond stress in N/mm² in cold condition according to

Table C2 considering concrete class, rebar diameter, drilling method and the bond


conditions according to EN 1992-1-1:2004+AC:2010

 γ_{c} Partial factor EN 1992-1-1:2004+AC:2010 $\gamma_{M,fi}$ Partial factor EN 1992-1-2:2004+AC:2008

For evidence under fire exposure the anchorage length shall be calculated according to EN 1992-1-1:2004+AC:2010 Equation 8.3 using the temperature-dependent ultimate bond stress fbd,fi.

Figure C1: Example graph of reduction factor $k_{\rm fi}$ (θ)

Concrete strength class C20/25 for good bond conditions



Injection System VMU plus for rebar connections

Performances

Design value of ultimate bond stress f_{bd,fi} under fire exposure for rebar

Annex C2



Table C4: Characteristic tension strength in case of fire for tension anchor ZA, concrete strength class C12/15 to C50/60, acc. to Technical Report TR 020

Tension anchor ZA				M12	M16	M20	M24	
Steel failure								
Steel, zinc plated								
Characteristic tension strength	R30	- σ _{Rk,s,fi}	[N/mm²]	20				
	R60			15				
	R90			13				
	R120				1	0		
Stainless steel A4, HCR								
Characteristic tension strength	R30		[N/mm²]	30				
	R60			25				
	R90	$\sigma_{Rk,s,fi}$			2	0		
	R120				1	6		

Design value of the tension strength $\sigma_{\text{Rd},s,\text{fi}}$ under fire exposure for tension anchor ZA

The design value of the steel strength $\sigma_{\text{Rd,s,fi}}$ under fire exposure will be calculated by the following equation:

$$\sigma_{Rd.s.fi} = \sigma_{Rk.s.fi} / \gamma_{M.fi}$$

with:

 $\sigma_{\text{Rk},s,\text{fi}}$ $\;$ characteristic steel strength acc. to Table C4

γ_{M,fi} partial factor under fire exposure acc. to EN 1992-1-2:2004+AC:2008

Injection System VMU plus for rebar connections	
Performances Steel strength for tension anchor ZA under fire exposure	Annex C3